
























PARSHWANATH GROUP OF INDUSTRIES

**Plot No. I - 5617, Phase - 2, Vatva, G.I.D.C.
Ahmedabad - 382445, Gujarat, India**

Telephone : +(91)-(79)-40083231/40085401/40085400

Email : inquiry@parshwadyes.com

Reactive Cold Dyes		FASTNESS PROPERTIES				
		Light	Washing	Perspiration	Hypochlorite	Dischargeability
Red M5B Red - 2		4-5	4-5	3-4	1	P
Red M8B Red - 11		4-5	4-5	2	4	P
Magenta MB Violet - 13		4-5	5	4-5	1	F
Orange M2R Orange - 4		5	5	4	4	P
Orange M2RJ		3-4	4	4	4-5	P
Gol. Yellow MR Yellow - 44		5	4-5	4	1	P
Yellow MR EX H/C Yellow - 44		5	4-5	4	1	P
Yellow M3R Yellow - 36		6	5	4	2	G
Yellow M4R Orange - 14		5	4-5	4	1	P
Yellow M8G Yellow - 86		6	4-5	4-5	1	G
Yellow M4G Yellow - 22		6	4	5	1	G
Yellow MGR Yellow - 7		6	5	4-5	4-5	P
Violet C4R Violet - 12		4	3	4	1	P
Violet C2R Violet - 14		3-4	3	4	1	P
Blue MR Blue - 4		6	5	5	2	P
Blue M2R Blue - 81		6	5	4-5	1	P
Blue M2R H/C Blue - 81		6	5	4-5	1	P
Navy Blue M3R Blue - 9		5	4-5	3	3	P
Blue M4GD H/C Blue - 168		6	5	3-4	2	P
Tur. Blue MGN Blue - 140		6	4	4	2-3	P
Tur. Blue Ha5G Blue - 71		6	3-4	4-5	3-4	P